

## “Anaconda – Copper Abrasive Specifications”

Rev 2 – Dated: 11/30/2018

Written By: IA

Approved by: SK/IA/JA

Pages 1 of 1

Grade	Tyler/US	Gradation Specifications	Recommended Applications
<b>Medium (12-40)</b>	#8 /8 #10/12 #14/16 #20/20 #28/30 #35/40 PAN	0 4-14 30-45 40-55 14-24 2-9 0-2	Mill scale, medium rust and paint stripping, ships, bridges, general usage.
<b>Fine (20-40)</b>	#8 /8 #14/16 #20 /20 #28/30 #35/40 #48/50 #65/70 PAN	0 0-3 0-15 35-70 10-50 0-25 0-5 0-5	New Steel, mill scale light rust and paint stripping, frames, trucks.
<b>Extra Fine (30-60)</b>	#14/16 #20 /20 #28/30 #65/70 #100/100 PAN	0 0-2 0-5 70-98 0-15 0-15	New Steel, mill scale light rust and paint stripping, frames, trucks.