

## “Coffeen – Coal Abrasive Specifications”

Rev 2 – Dated: 7/31/2020

Written By: EH

Approved by: JV/JF

Pages 1 of 1

<b>Grade</b>	<b>Tyler/US</b>	<b>Gradation Specifications</b>	<b>Recommended Applications</b>
<b>Utility (10–40)</b>	#8 /8	0-15	Heavy rust, ships, barges, tanks, concrete, heavy paint coating removal
	#10/12	50-80	
	#14/16	5-25	
	#20 /20	0-10	
	PAN	0-5	
<b>Medium (12–40)</b>	#8 /8	0	Mill scale, medium rust and paint stripping, ships, bridges, general usage.
	#10/12	4-14	
	#14/16	30-45	
	#20 /20	25-35	
	#28/30	14-24	
	#35/40	2-9	
<b>Fine (20–40)</b>	PAN	0-2	New Steel, mill scale light rust and paint stripping, frames, trucks.
	#10/12	0-1	
	#14/16	0-3	
	#20 /20	0-25	
	#28/30	35-70	
	#35/40	15-50	
	#48/50	0-25	
<b>Extra Fine (30–60)</b>	#65/70	0-5	New Steel, mill scale light rust and paint stripping, frames, trucks.
	PAN	0-5	
	#14/16	0	
	#20 /20	0-2	
	#28/30	0-5	
	#65/70	70-98	
	#100/100	0-10	
	PAN	0-5	