

“Galvestone – Copper Abrasive Specifications”

Rev 1 – Dated: 12/11/2017

Written By: IA

Approved by: VP/JV

Pages 1 of 1

Grade	Tyler/US	Gradation Specifications	Recommended Applications
Utility (10-40)	#6 /6 #8 /8 #10/12 #14/16 #20/20 PAN	0-2 0-20 50-80 5-25 0-10 0-5	Heavy rust, ships, barges, tanks, concrete, heavy paint coating removal
Medium (12-40)	#8 /8 #10/12 #14/16 #20/20 #28/30 #35/40 PAN	0 4-14 30-45 25-35 14-24 2-9 0-2	Mill scale, medium rust and paint stripping, ships, bridges, general usage.
Fine (20-40)	#8 /8 #10/12 #14/16 #20/20 #28/30 #35/40 #48/50 #65/70 PAN	0 0-1 0-3 0-25 35-70 10-50 0-30 0-7 0-5	New Steel, mill scale light rust and paint stripping, frames, trucks.
Extra Fine (30-60)	#14/16 #20/20 #28/30 #65/70 #100/100 PAN	0 0-2 0-5 70-98 0-10 0-5	New Steel, mill scale light rust and paint stripping, frames, trucks.