

“Harvey – Copper Abrasive Specifications”

Rev 2 – Dated: 3/17/2020

Written By: EH

Approved by: JV

Pages 1 of 1

Grade	Tyler/US	Gradation Specifications	Recommended Applications
Utility (10-40)	#6 /6 #8 /8 #10/12 #14/16 #20 /20 #28/30 #35/40 PAN	0 0-5 20-50 20-50 10-20 0-15 0-8 0-5	Heavy rust, ships, barges, tanks, concrete, heavy paint coating removal
Medium (12-40)	#6 /6 #8 /8 #10/12 #14/16 #20 /20 #28/30 #35/40 #65/70 PAN	0 0-1 0-15 20-45 15-45 10-30 0-15 0-15 0-5	Mill scale, medium rust and paint stripping, ships, bridges, general usage.
Fine (20-40)	#8 /8 #10/12 #14/16 #20 /20 #28/30 #35/40 #65/70 PAN	0 0-2 0-15 5-35 20-45 15-35 5-20 0-8	New Steel, mill scale light rust and paint stripping, frames, trucks.