

“Tamko Headlap Specifications”

Rev 2 – Dated: 5/11/2021

Written By: EH

Approved by: JV

Pages 1 of 1

Sieve Size	Minimum	Maximum
US #8	0.0%	0.1%
US #12	4.0%	10.0%
US #16	30.0%	45.0%
US #20	20.0%	40.0%
US #30	10.0%	30.0%
US #40	2.0%	9.0%
Pan	0.0%	2.0%

- **Bulk Density greater than 85 lbs/ft³**
- **Moisture no more than 1% by weight**
- **Translucency (opacity) less than 10% (3 tab shingles only)**
- **Oil at rate of 1.5 pints/ton**
- **Notify Quality Control of any rust immediately**