

## “Zahori Specifications”

Rev 1 – Dated: 12/04/2017

Written By: IA

Approved by: VP/JV

Pages 1 of 1

<b>Sieve Size</b>	<b>Minimum</b>	<b>Maximum</b>
<b>US #20</b>	<b>0.0%</b>	<b>0.0%</b>
<b>US #30</b>	<b>0.0%</b>	<b>4.0%</b>
<b>US #40</b>	<b>5.0%</b>	<b>16.0%</b>
<b>US #50</b>	<b>9.0%</b>	<b>25.0%</b>
<b>US #60</b>	<b>7.0%</b>	<b>23.0%</b>
<b>US #70</b>	<b>5.0%</b>	<b>12.0%</b>
<b>US #80</b>	<b>5.0%</b>	<b>15.0%</b>
<b>US#120</b>	<b>10.0%</b>	<b>19.0%</b>
<b>Pan</b>	<b>5.0%</b>	<b>35.0%</b>

### NOTES:

- **Mesh #20 must be “0%” – Breaks product and causes bad appearance**
- **Mesh #120 & PAN must meet requirements – If not met fails glued testing.**
- **Galveston Blend ~ 50/50 of 3060/-60.**